

A2017押出・引抜丸棒

Al-Cu系・熱処理合金／銅(Cu)を多く含むため耐食性はよくないが、強度が高く構造用材として使用される。鍛造用素材としても使用される。



在庫サイズ一覧

定尺		調質	外径公差 (mm)	寸法 増値
外径 (mm)	長さ (mm)			
20	2000	T4(引抜)	-0.1 ~ +0	25
21				25
22				25
24				25
25				15
28			15	
29			15	
30			0	
32			0	
33			-0.12 ~ +0	0
35				0
36				0
37				0
38				0
40				0
42				0
44			-0.14 ~ +0	0
45				0
46				0
48				0
49				0
50				0
51			-0.15 ~ +0.105	0
52				0
55				0
58				0
60				20
65			2000	T4(押出)
70	20			

定尺		調質	外径公差 (mm)	寸法 増値	
外径 (mm)	長さ (mm)				
75	2000	T4(押出)	±0.61	30	
80				30	
85				30	
90				30	
95				30	
100				35	
105			±0.86	35	
110				35	
115				35	
120				35	
125				45	
130				45	
140				45	
150				65	
160				±1.12	65
170					65
180			90		
190			90		
200			120		
210			±1.37		120
220				120	
230				120	
240				120	
250			±1.88	150	
260				150	
270				150	
280				150	
290				150	
300				150	

《加工案内》

加工方法	参照頁
丸鋸切断 	P31
バンドソー切断 	P31